



P.O.Box: 14155 – 5345 ,Tehran , Iran

Tel: (+9821) 44207691

www.3p1.ir

Technical Data sheet

Yellow Masterbatch 5564

Yellow masterbatch 5564 is a PE based Masterbatch suitable for all conventional processes.

Product Name:	5564 – a.r
Appearance:	Granual
Company:	3P
Heat Resistance:	300 °C
Light Fastness:	7 – 8
Recommende:	1% ~ 5%

Product Description

Yellow masterbatch 5564 is is a good dispersed polyethylene based Masterbatch for all kind of extruded and molded goods.

Yellow masterbatch 5564 is has a very high color strength and good flow properties and is recommended product for thin films, where high opacity is required

Information and test method

Property	Test Method	Measured Value	Unit
Pigment Content	ASTM D-1505/D-792	30±3	%0
Density	ASTM D-1505/D-792	0.6	Grams/cc
Melt flow index	ASTM D-1238	15	Gram /10min

Notice

The Information presented herein is presented in good faith and to the best of our knowledge is true and accurate

Packaging

5564 bags should be stored in a dry and cool place below 35°C,protected from sunlight & tightly closed to avoid contamination .

5564 is packed in special 25kg bags.